



## **REGIONAL LABORATORY**

## **TEXTILES COMMITTEE**

(Ministry of Textiles, Government of India)
Textile Testing & Technical Services

21 - J, KVR Complex, 2nd Floor, 80 Feet Road, KARUR - 639 002. Tel: 04324 238610, Tel/Fax: 274871 E.mail: tckarur@gmail.com, krr.tc@nic.in



## **TEST REPORT**

Test Report Number

1913

Date

08-11-2019

Name of the Party

Sample Forwarding Letter No & Date: No: nil date:08-11-2019

Date of Receipt of Sample

Buyer's / Importer's Name and Address

Date of Testing 08-11-2019

Customer Sample No Sample Description Sample Color Lab Sample No

Fabric

CCO-1913

ULR Number: ULR-TC-810819000001368P TESTRESULTS

Colour Fastness to Washing at 40°C

(ISO: 105 C-10 A1: 2006)

( Grey Scale rating ) Change in Colour

Staining on Cotton 4

Colour Fastness to Rubbing (ISO 105 X 12 - 2016)

Orev scale rating (warp & weft)

DRY

4

Dimensional Changes (%) after Home Laundering at 30°C \* (ISO 5077-1984, 6330-2008) using 1.8 Kg Load

(Machine wash, Normal Low Tumble Dry ) 1 Cycle

Warp

-9.3

Weft

0.0 (Nil)

\* Partialy accredited parameter

V

Not

Page 1 of 1

Complaints if any are to be reached within 45 days of issue of Test Report

Signature and seal of Officer

् गुणवता आश्वासन अधिकारी (प्र**या**गशाला

R. BALU

QUALITY ASSURANCE OFFICER LAB

ISO: 17025 Accredited Laboratory

Sample is not drawn by Textiles Committee.	Cicy	Journal Hauring	Pilling Rating	Blue Wool Rating
Results relate only to the samples tested.	Change in colour	Staining		8. Outstanding
	5. Excellent	5 No Staining		
consent of the Textiles Committee.	4. Good	4. Slight Staining		7.Excellent 6.Very Good
Please quote Test Report No. and date for all future correspondence		Noticeable Staining	3. Moderate Pilling	5. Fairly Good 4.Good
Sample is conditioned and tested at a temp.of 27±2°C (Instead of 20/21±2/1°C)	2. Poor	Considerable Staining	2. Severe Pilling	3. Fair 2.Poor
and 65+2%RH wherever ASTIVI/AATCC/ISO methods adopted			1. Very Severe Pilling	1 Very Poor
Complaints, if any, are to be received within 45 days of issue of the test report.	1. Very Poor	Extensive Staining	1. Very Devere 1 ming	1. Very Foot

Headoffice:TextilesCommittee (Ministry of Textiles,Government of India), P.Balu Road, Prabhadevi Chowk, Prabhadevi, MUMBAI-400025,Tel:091+022+66527500 Fax:091+022+66527554 E-mail:tclabmumbai@gmail.com