



REGIONAL LABORATORY

TEXTILES COMMITTEE

(Ministry of Textiles, Government of India) **Textile Testing & Technical Services**

> 21 - J. KVR Complex, 2nd Floor, 80 Feet Road, KARUR - 639 002. Tel: 04324 238610, Tel / Fax: 274871 E.mail: tckarur@gmail.com, krr.tc@nic.in



TEST REPORT

Test Report Number	1914	Date	08-11-2019	
Name of the Party			3000	
Sample Forwarding Letter No & Date: Date of Receipt of Sample Buyer's / Importer's Name and Address	No: nil date:08-11-2019 08-11-2019		3888	
Date of Testing	08-11-2019		1 2 VVD V	
Customer Sample No	Sample Description	Sam	ple Color Lab Sample No	

Customer Sample No	Sample Descripti	on	Sample Color	Lab Sample No
	Fabric			CCO-1914
ULR Number: ULR-TC-810819000001369P		TESTRESULTS		
Colour Fastness to Washing at	40°C			
(ISO: 105 C-10 A1 : 2006)				
(Grey Scale rating) Change	4			
Staining on Cotton		4		
Colour Fastness to Rubbing	(ISO 105 X 12 - 2016)	DRY	WET	
Grey scale rating (warp & weft)		4	4	
Dimensional Changes (%) after	er Home Laundering at 30°C	C *		
(ISO 5077-1984, 6330-2008)				
(Machine wash, Normal Low				
Warp		-9.5		
Weft		-2.9		

Page 1 of 1

[-] Shrinkage, *Not accredited parameter

Complaints if any are to be reached within 45 days of issue of Test Report

[+] Elongation

Signature and seal of Officer

गुणवत्ता ऑंश्वासन अधिकारी (प्रकागशाला R. BALU

QUALITY ASSURANCE OFFICER (LAB)

ISO: 17025 Accredited Laboratory

Grey Scale Rating Sample is not drawn by Textiles Committee. Blue Wool Rating Pilling Rating Change in colour Results relate only to the samples tested. 5. No Pilling 8. Outstanding This test report is not to be published in any form without the explicit written 5. Excellent 5. No Staining 7.Excellent 6.Very Good 4. Slight Pilling consent of the Textiles Committee. 4. Good 4. Slight Staining Please quote Test Report No. and date for all future correspondence 3. Moderate Pilling 5. Fairly Good 4. Good 3. Noticeable Staining 3. Fair Sample is conditioned and tested at a temp.of 27±2°C (Instead of 20/21±2/1°C) 2. Severe Pilling 3. Fair 2. Poor 2. Considerable Staining 2. Poor and 65±2%RH wherever ASTM/AATCC/ISO methods adopted 1. Very Poor 1. Very Severe Pilling 1. Extensive Staining Complaints, if any, are to be received within 45 days of issue of the test report. 1. Very Poor

Headoffice: Textiles Committee (Ministry of Textiles, Government of India), P.Balu Road, Prabhadevi Chowk,