



**REGIONAL LABORATORY**  
**TEXTILES COMMITTEE**

(Ministry of Textiles, Government of India)

**Textile Testing & Technical Services**

21 - J, KVR Complex, 2nd Floor,

80 Feet Road, KARUR - 639 002.



Tel : 04324 238610, Tel / Fax : 274871

E.mail : [tckarur@gmail.com](mailto:tckarur@gmail.com), [krr.tc@nic.in](mailto:krr.tc@nic.in)



**TEST REPORT**

<b>Test Report Number</b>	<b>1915</b>	<b>Date</b>	<b>08-11-2019</b>
---------------------------	-------------	-------------	-------------------

Name of the Party	[REDACTED]	 
Sample Forwarding Letter No & Date :	No: nil date:08-11-2019	
Date of Receipt of Sample	08-11-2019	
Buyer's / Importer's Name and Address	[REDACTED]	
Date of Testing	08-11-2019	

<b>Customer Sample No</b>	<b>Sample Description</b>	<b>Sample Color</b>	<b>Lab Sample No</b>
	Fabric		<b>CCO-1915</b>


<b>ULR Number : ULR-TC-810819000001370P</b>	<b>TEST RESULTS</b>
---	---------------------

<b>Colour Fastness to Washing at 40°C</b>			
( ISO: 105 C-10 A1 : 2006 )			
( Grey Scale rating )	Change in Colour	4	
	Staining on Cotton	4	
<b>Colour Fastness to Rubbing</b>	( ISO 105 X 12 - 2016 )	DRY	WET
<b>Grey scale rating (warp &amp; weft)</b>		4	4
<b>Dimensional Changes ( % ) after Home Laundering at 30°C *</b>			
( ISO 5077-1984, 6330-2008 ) using 1.8 Kg Load			
( Machine wash, Normal Low Tumble Dry ) 1 Cycle			
	Warp	-6.7	
	Weft	-2.3	

\* Not accredited parameter

Page 1 of 1

Complaints if any are to be reached within 45 days of issue of Test Report

  
**Signature and seal of Officer**  
आर. बालू  
गुणवत्ता आश्वासन अधिकारी (प्रबन्धशाखा)  
R. BALU  
QUALITY ASSURANCE OFFICER (LAB)

**ISO : 17025 Accredited Laboratory**

Sample is not drawn by Textiles Committee. Results relate only to the samples tested. This test report is not to be published in any form without the explicit written consent of the Textiles Committee. <b>Please quote Test Report No. and date for all future correspondence</b> Sample is conditioned and tested at a temp. of 27±2°C (Instead of 20/21±2/1°C) and 65±2%RH wherever ASTM/AATCC/ISO methods adopted <b>Complaints, if any, are to be received within 45 days of issue of the test report.</b>	Grey Scale Rating		Pilling Rating	Blue Wool Rating
	Change in colour	Staining		
	5. Excellent	5. No Staining	5. No Pilling	8. Outstanding
	4. Good	4. Slight Staining	4. Slight Pilling	7. Excellent 6. Very Good
	3. Fair	3. Noticeable Staining	3. Moderate Pilling	5. Fairly Good 4. Good
	2. Poor	2. Considerable Staining	2. Severe Pilling	3. Fair 2. Poor
	1. Very Poor	1. Extensive Staining	1. Very Severe Pilling	1. Very Poor