



REGIONAL LABORATORY
TEXTILES COMMITTEE
(Ministry of Textiles, Government of India)
Textile Testing & Technical Services

21 - J, KVR Complex, 2nd Floor,
80 Feet Road, KARUR - 639 002.
Tel : 04324 238610, Tel / Fax : 274871

E.mail : tckarur@gmail.com, krr.tc@nic.in



TEST REPORT

Test Report Number


1916

Date

08-11-2019

Name of the Party

[Redacted Name]



Sample Forwarding Letter No & Date :

No: nil date:08-11-2019

Date of Receipt of Sample

08-11-2019

Buyer's / Importer's Name and Address

Date of Testing

08-11-2019

Customer Sample No	Sample Description	Sample Color	Lab Sample No
--------------------	--------------------	--------------	---------------

Fabric

CCO-1916

ULR Number : ULR-TC-810819000001371P

TEST RESULTS

Colour Fastness to Washing at 40°C

(ISO: 105 C-10 A1 : 2006)

(Grey Scale rating) Change in Colour
Staining on Cotton

3-4
4

Colour Fastness to Rubbing (ISO 105 X 12 - 2016)

Grey scale rating (warp & weft)

DRY WET
4 4

Dimensional Changes (%) after Home Laundering at 30°C *

(ISO 5077-1984, 6330-2008) using 1.8 Kg Load

(Machine wash, Normal Low Tumble Dry) 1 Cycle

Warp -6.1
Weft -0.8

* Not Accredited parameter

Page 1 of 1

Complaints if any are to be reached within 45 days of issue of Test Report

Signature and seal of Officer

भार. बालू
गुणवत्ता आश्वासन अधिकारी (प्रकाशशाला)
R. BALU
QUALITY ASSURANCE OFFICER (LAB)

ISO : 17025 Accredited Laboratory

Sample is not drawn by Textiles Committee.

Results relate only to the samples tested.

This test report is not to be published in any form without the explicit written consent of the Textiles Committee.

Please quote Test Report No. and date for all future correspondence

Sample is conditioned and tested at a temp. of 27±2°C (Instead of 20/21±2/1°C) and 65±2%RH wherever ASTM/AATCC/ISO methods adopted

Complaints, if any, are to be received within 45 days of issue of the test report.

Grey Scale Rating		Pilling Rating	Blue Wool Rating
Change in colour	Staining		
5. Excellent	5. No Staining	5. No Pilling	8. Outstanding
4. Good	4. Slight Staining	4. Slight Pilling	7. Excellent 6. Very Good
3. Fair	3. Noticeable Staining	3. Moderate Pilling	5. Fairly Good 4. Good
2. Poor	2. Considerable Staining	2. Severe Pilling	3. Fair 2. Poor
1. Very Poor	1. Extensive Staining	1. Very Severe Pilling	1. Very Poor

Headoffice: Textiles Committee (Ministry of Textiles, Government of India), P. Balu Road, Prabhadevi Chowk, Prabhadevi, MUMBAI-400025 Tel: 091+022+66527500 Fax: 091+022+2527751